

Non-asbestos Sheet
CAZ-NCAF 432,433,434

Joint Sheets

CONSTRUCTION:

CAZ NCAF Non-asbestos sheet is made from synthetic fibre, natural rubber, filling material and dye, compressed and calendered under high temperature and pressure into a sheet form. It eliminates asbestos-rubber sheet essentially and thoroughly.

PARAMETER:

| Item | Style | | |
|------------------------------|------------------------------------------------------------------------------|--------------------------------------------------|--------------------------------------------------|
| | 432 | 433 | 434 |
| Density g/cm ³ | 1.8~2.0 | 1.8~2.0 | 1.8~2.0 |
| Tensile strength ≥Mpa | 6 | 9 | 12.5 |
| Compressibility ≥% | 12±5 | 12±5 | 12±5 |
| Recovery ≥% | 40 | 45 | 45 |
| Aging coefficient | 0.9 | 0.9 | 0.9 |
| Stress relaxation ≤% | 45 | 45 | 45 |
| Steam Sealing | Tmax: 200°C Pmax: 2~3Mpa 30min no shock | Tmax: 300°C Pmax: 4~5Mpa 30min no shock | Tmax: 400°C Pmax: 8~9Mpa 30min no shock |
| Tmax: °C | 200 | 300 | 400 |
| Pmax: Mpa | 1.5 | 3.0 | 5.0 |
| Resistance to media | Water, seawater, steam, fuel, gases, salt solutions and many other media. | | |

Normal colour: Black with some white, Blue or Green-white etc.
Available with tin steel, copper, SS304 etc. wire mesh insertion (**43*M**)
Also available with anti-stick (**43*S**) or graphite coating (**43*G**)
With your logo on request.

DIMENSIONS:

Sheets:

Thickness: 0.4~5mm
2000×1500mm; 1500×4000mm; 1500×1500mm; 1350×1500mm
1500×1000mm; 1270×1270mm; 3810×1270mm

Cut gaskets:

G432, G433, G434

Dimensions according to drawings or and standards

